Hewitt
HERITAGE FABRICS

Q143/0554

Custom Code
5211.42.0090

Production/Availability
TO ORDER

Price for Sample
Ex-Works £14.50 per meter

Price for Production
Ex-Works £14.50 per meter

Yarn Size
Ne 8/1 x Nm 16

Yarn Count
TURKISH COTTON x FRENCH LINEN

Description
COTTON WARP / LINEN WEFT

Width
75.2 cm
Usable Width
75.2 cm

Weight
428 Gr/m2
14.10 Oz/y2

Section	Test Method		Units	Actual	Remarks
Fastness To Laundering	BS EN ISO C06-A2 @ 30'c	Colour Change	On Scale 5	4 - 5	@ 30 Degrees
		Staining	On Scale 5	4 - 5	@ 30 Degrees
Acidic Persperation	BS EN ISO 105 - E04	Colour Change	On Scale 5	4 - 5	
		Staining	On Scale 5	4 - 5	
Alkiline Persperation	BS EN ISO 105 - E04	Colour Change	On Scale 5	4 - 5	
		Staining	On Scale 5	4 - 5	
Crocking	BS EN ISO 105 -X12	Dry	On Scale 5	3 - 4	
		Wet	On Scale 5	1 - 2	
Formaldehyde Free	BS EN ISO 14184-1: 2011				Not Detected
Formaldehyde Released	BS EN ISO 14184-2: 2011				Not Detected
Ph	BSEN ISO				
Tensile Strength	BS EN ISO13934-2		WARP	1464	Dry Fabric
			WEFT	590	Dry Fabric
Tear Strength	BS EN ISO 13937-1		WARP	34	Dry Fabric
			WEFT	27	Dry Fabric
Seam Slipage	BS EN ISO 13936 -1: 2004		WARP		Dry Fabric
			WEFT		Dry Fabric
Dimensional Change	BS EN ISO 6330 washed @ 30 degrees/ line dry		WARP	2 - 4%	1st @ 30 Degrees
			WEFT	0.5 - 1.5%	1st @ 30 Degrees
			WARP		2nd @ 30 Degrees
			WEFT		2nd @ 30 Degrees
Weight	BS EN ISO 12127		Gr/m2	428	Unwashed
			Gr/m2		1 X 30 Degrees Wash
			Oz/y2		Unwashed
			Oz/y2		1 X 30 Degrees Wash

Indigo Type
Dystar GOTS Version 4 Approved 40% Pre-Reduced

Type
Rope Dyed

Denim Notes
THIS IS A SOFT DENIM WHICH IS REMINISCENT OF WOOL WITH A SIMILAR DRAPE. DUE TO THE NATURE OF LINEN THERE WILL LEVEL OF TWIST WHEN WASHED

Season

- S /S 21
- A /W 21
- S /S 22
- A /W 22
- S /S 23
- A/W 23

Washing Care

All Fabrics are **"MADE IN ENGLAND"**